

An independent testing laboratory specialising in the testing of cementitious materials

PREPARED FOR TITAN CEMENT Ltd. HULL

REPORT REFERENCE	Titan	132
CLIENT REFERENCE	PRISM	2024
SHIP REFERENCE	"8-24	
SAMPLE	ORDINARY PORTLAND CEMENT	
DATE OF RECEIPT OF SAMPLE	10-Oct-24	
DATE OF TESTS	10-Oct-24	to 7-Nov-24
DATE OF REPORT	13-Nov-24	

ALL RESULTS ARE BASED ON SAMPLE RECEIVED FROM THE CLIENT: TESTED AS RECEIVED.

CHEMICAL COMPOSITION :- by mass, as received

Density	3160 kg/m ³	(BSEN 196-6:2010)
Fineness	4280 cm ² /g	(BSEN 196-3:2016)
Standard Consistence	29.5 %	(BSEN 196-3:2016)
Initial Setting Time	194 mins	(BSEN 196-3:2016)
Soundness	1.0 mm	(BSEN 196-3:2016)

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016)

AT 2 DAYS	32.4 MPa	(Mean of 6 results, none discarded)
AT 7 DAYS	47.4 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	60.8 MPa	(Mean of 6 results, none discarded)


CHEMICAL COMPOSITION :- by mass, as received

K ₂ O	0.49 %	(BSEN 196-2:2013)
Na ₂ O	0.20 %	(BSEN 196-2:2013)
Na ₂ O (eq)	0.52 %	(BSEN 196-2:2013)
Chloride	0.03 %	(BSEN 196-2:2013)

END OF REPORT

SIGNED:

Certificate signed by:



✓ S. Burton A.M.I.C.T

Technical Manager

J.M. Burton

Quality Manager