



An independent testing laboratory specialising in the testing of cementitious materials

PREPARED FOR TITAN CEMENT Ltd. HULL			
REPORT REFERENCE	Titan	137	
CLIENT REFERENCE	CUBES	2024	
SHIP REFERENCE	"1-25		
SLUMP	ORDINARY PORTLAND CEMENT		
DATE OF RECEIPT OF SAMPLE	20-Feb-25		
DATE OF TESTS	20-Feb-25	to	20-Mar-25
DATE OF REPORT	20-Mar-25		

ALL RESULTS ARE BASED ON SAMPLE RECEIVED FROM THE CLIENT: TESTED AS RECEIVED.						
COMPRESSIVE STRENGTH: Concrete Cubes						
AT 3 DAYS	34.4	35.7	35.0	Average	35.0 MPa	BSEN 12390-2: 2019
AT 7 DAYS	45.8	43.5	43.5	Average	44.3 MPa	BSEN 12390-2: 2019
AT 28 DAYS	55.1	52.8	55.9	Average	54.6 MPa	BSEN 12390-2: 2019

SLUMP	60	mm
-------	----	----

Note:- The slump test was carried out on 20/02/2025 at "9.30 as per BSEN 12350-2: 2019 by R.Burnett A ten litre mixer was used for the the mixing of the sample, sampling was carried out in accordance with BSEN 12350-1: 2019. The slump cone was filled and the test carried out 2 mins +/- 30s from the end of mixing. The mixing, sampling and slump test were carried out at Kirton Concrete Services Ltd's. laboratory. The slump was a true slump.

END OF REPORT

KIRTON CONCRETE SERVICES LTD

SIGNED:.....

Certificate signed by: ✓ S.Burton A.M.I.C.T
Technical Manager

J.M. Burton
Quality Manager