

An independent testing laboratory specialising in the testing of cementitious materials

PREPARED FOR TITAN CEMENT Ltd. HULL

REPORT REFERENCE	Titan	137
CLIENT REFERENCE	PRISM	2024
SHIP REFERENCE	"1-25	
SAMPLE	ORDINARY PORTLAND CEMENT	
DATE OF RECEIPT OF SAMPLE	20-Feb-25	
DATE OF TESTS	20-Feb-25	to 20-Mar-25
DATE OF REPORT	20-Mar-25	

ALL RESULTS ARE BASED ON SAMPLE RECEIVED FROM THE CLIENT: TESTED AS RECEIVED.

CHEMICAL COMPOSITION :- by mass, as received

Density	3150 kg/m ³	(BSEN 196-6:2010)
Fineness	4380 cm ² /g	(BSEN 196-3:2016)
Standard Consistance	30.0 %	(BSEN 196-3:2016)
Initial Setting Time	203 mins	(BSEN 196-3:2016)
Soundness	1.0 mm	(BSEN 196-3:2016)

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016)

AT 2 DAYS	36.7 MPa	(Mean of 6 results, none discarded)
AT 7 DAYS	50.7 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	66.9 MPa	(Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass, as received

K ₂ O	0.51 %	(BSEN 196-2:2013)
Na ₂ O	0.25 %	(BSEN 196-2:2013)
Na ₂ O (eq)	0.59 %	(BSEN 196-2:2013)
Chloride	0.03 %	(BSEN 196-2:2013)

END OF REPORT

SIGNED:

Certificate signed by:



✓ S. Burton A.M.I.C.T

Technical Manager

J.M. Burton

Quality Manager