

An independent testing laboratory specialising in the testing of cementitious materials

## PREPARED FOR TITAN CEMENT Ltd. HULL

REPORT REFERENCE	Titan	138
CLIENT REFERENCE	PRISM	2025
SHIP REFERENCE	"2-25	
SAMPLE	ORDINARY PORTLAND CEMENT	
DATE OF RECEIPT OF SAMPLE	18-Mar-25	
DATE OF TESTS	18-Mar-25	to 15-Apr-25
DATE OF REPORT	22-Apr-25	

ALL RESULTS ARE BASED ON SAMPLE RECEIVED FROM THE CLIENT: TESTED AS RECEIVED.  
CHEMICAL COMPOSITION :- by mass, as received

Density	3100 kg/m <sup>3</sup>	(BSEN 196-6:2010 )
Fineness	4220 cm <sup>2</sup> /g	(BSEN 196-3:2016)
Standard Consistance	30.0 %	(BSEN 196-3:2016)
Initial Setting Time	205 mins	(BSEN 196-3:2016)
Soundness	1.0 mm	(BSEN 196-3:2016)

## COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016)

AT 2 DAYS	35.7 MPa	(Mean of 6 results,none discarded)
AT 7 DAYS	52.0 MPa	(Mean of 6 results,none discarded)
AT 28 DAYS	66.1 MPa	(Mean of 6 results,none discarded)

## CHEMICAL COMPOSITION :- by mass, as received

K <sub>2</sub> O	0.48 %	(BSEN 196-2:2013)
Na <sub>2</sub> O	0.29 %	(BSEN 196-2:2013)
Na <sub>2</sub> O (eq)	0.61 %	(BSEN 196-2:2013)
Chloride	0.04 %	(BSEN 196-2:2013)

END OF REPORT

SIGNED:

Certificate signed by:



✓ S.Burton A.M.I.C.T

Technical Manager

J.M. Burton

Quality Manager