

An independent testing laboratory specialising in the testing of cementitious materials

PREPARED FOR TITAN CEMENT Ltd. HULL

REPORT REFERENCE	Titan	141
CLIENT REFERENCE	PRISM	2025
SHIP REFERENCE	"5-25	
SAMPLE	ORDINARY PORTLAND CEMENT	
DATE OF RECEIPT OF SAMPLE	11-Jun-25	
DATE OF TESTS	11-Jun-25	to 9-Jul-25
DATE OF REPORT	15-Jul-25	

ALL RESULTS ARE BASED ON SAMPLE RECEIVED FROM THE CLIENT: TESTED AS RECEIVED.
CHEMICAL COMPOSITION :- by mass, as received

Density	3150 kg/m ³	(BSEN 196-6:2010)
Fineness	4380 cm ² /g	(BSEN 196-3:2016)
Standard Consistance	29.5 %	(BSEN 196-3:2016)
Initial Setting Time	199 mins	(BSEN 196-3:2016)
Soundness	2.0 mm	(BSEN 196-3:2016)

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016)

AT 2 DAYS	32.0 MPa	(Mean of 6 results,none discarded)
AT 7 DAYS	48.7 MPa	(Mean of 6 results,none discarded)
AT 28 DAYS	62.1 MPa	(Mean of 6 results,none discarded)

CHEMICAL COMPOSITION :- by mass, as received

K ₂ O	0.46 %	(BSEN 196-2:2013)
Na ₂ O	0.24 %	(BSEN 196-2:2013)
Na ₂ O (eq)	0.54 %	(BSEN 196-2:2013)
Chloride	0.04 %	(BSEN 196-2:2013)

END OF REPORT

SIGNED:

Certificate signed by:



✓ S.Burton A.M.I.C.T

Technical Manager

J.M. Burton

Quality Manager