

An independent testing laboratory specialising in the testing of cementitious materials

## PREPARED FOR TITAN CEMENT Ltd. HULL

REPORT REFERENCE	Titan	144
CLIENT REFERENCE	CUBES	2025
SHIP REFERENCE	"8/25	
SLUMP	ORDINARY PORTLAND CEMENT	
DATE OF RECEIPT OF SAMPLE	27-Aug-25	
DATE OF TESTS	27-Aug-25	to 24-Sep-25
DATE OF REPORT	9-Oct-25	

ALL RESULTS ARE BASED ON SAMPLE RECEIVED FROM THE CLIENT: TESTED AS RECEIVED.

### COMPRESSIVE STRENGTH: Concrete Cubes

AT 3 DAYS	26.2	26.4	26.3	Average	26.3 MPa	BSEN 12390-2: 2019
AT 7 DAYS	34.9	35.1	34.7	Average	34.9 MPa	BSEN 12390-2: 2019
AT 28 DAYS	45.1	44.6	45.0	Average	44.9 MPa	BSEN 12390-2: 2019

SLUMP	70	mm
-------	----	----

Note:- The slump test was carried out on 11/09/2025 at 09:45:00 as per BSEN 12350-2: 2019 by A.longfellow A ten litre mixer was used for the the mixing of the sample, sampling was carried out in accordance with BSEN 12350-1: 2019. The slump cone was filled and the test carried out 2 mins +/- 30s from the end of mixing. The mixing, sampling and slump test were carried out at Kirton Concrete Services Ltd's. laboratory. The slump was a true slump.

END OF REPORT

KIRTON CONCRETE SERVICES LTD

SIGNED:.....

Certificate signed by: ✓ S.Burton A.M.I.C.T  
Technical Manager

J.M. Burton  
Quality Manager