

An independent testing laboratory specialising in the testing of cementitious materials

PREPARED FOR TITAN CEMENT Ltd. HULL

REPORT REFERENCE	Titan	145
CLIENT REFERENCE	CUBES	2025
SHIP REFERENCE	"9-25	
SLUMP	ORDINARY PORTLAND CEMENT	
DATE OF RECEIPT OF SAMPLE	28-Oct-25	
DATE OF TESTS	28-Oct-25	to 25-Nov-25
DATE OF REPORT	25-Nov-25	

ALL RESULTS ARE BASED ON SAMPLE RECEIVED FROM THE CLIENT: TESTED AS RECEIVED.

COMPRESSIVE STRENGTH: Concrete Cubes

AT 3 DAYS	28.1	28.0	26.5	Average	27.5 MPa	BSEN 12390-2: 2019
AT 7 DAYS	35.6	35.0	33.1	Average	34.6 MPa	BSEN 12390-2: 2019
AT 28 DAYS	43.3	46.0	43.5	Average	44.3 MPa	BSEN 12390-2: 2019

SLUMP	80	mm
-------	----	----

Note:- The slump test was carried out on 28/10/2025 at "14:45 as per BSEN 12350-2: 2019 by D.COOK A ten litre mixer was used for the the mixing of the sample, sampling was carried out in accordance with BSEN 12350-1: 2019. The slump cone was filled and the test carried out 2 mins +/- 30s from the end of mixing. The mixing, sampling and slump test were carried out at Kirton Concrete Services Ltd's. laboratory. The slump was a true slump.

END OF REPORT

KIRTON CONCRETE SERVICES LTD

SIGNED:.....

Certificate signed by: ✓ S.Burton A.M.I.C.T
Technical Manager

J.M. Burton
Quality Manager