



An independent testing laboratory specialising in the testing of cementitious materials

PREPARED FOR TITAN CEMENT Ltd. HULL

REPORT REFERENCE	Titan	146
CLIENT REFERENCE	CUBES	2025
SHIP REFERENCE	"10-25	
SLUMP	ORDINARY PORTLAND CEMENT	
DATE OF RECEIPT OF SAMPLE	18-Nov-25	
DATE OF TESTS	18-Nov-25	to 16-Dec-25
DATE OF REPORT	12-Feb-26	

ALL RESULTS ARE BASED ON SAMPLE RECEIVED FROM THE CLIENT: TESTED AS RECEIVED.

COMPRESSIVE STRENGTH: Concrete Cubes


AT 3 DAYS	30.3	30.0	31.0	Average	30.4 MPa	BSEN 12390-2: 2019
AT 7 DAYS	37.5	38.9	38.4	Average	38.3 MPa	BSEN 12390-2: 2019
AT 28 DAYS	50.4	50.0	51.2	Average	50.5 MPa	BSEN 12390-2: 2019


SLUMP	80	mm
-------	----	----

Note:- The slump test was carried out on **15/01/2026** at **01:12:00** as per BSEN 12350-2: 2019 by **D.COOK**. A ten litre mixer was used for the the mixing of the sample, sampling was carried out in accordance with BSEN 12350-1: 2019. The slump cone was filled and the test carried out 2 mins +/- 30s from the end of mixing. The mixing, sampling and slump test were carried out at Kirton Concrete Services Ltd's. laboratory. The slump was a true slump.

END OF REPORT



SIGNED:.....


Certificate signed by:  **S.Burton A.M.I.C.T**
Technical Manager

J.M. Burton
Quality Manager